



PLASTSU PLASTİK İML.İHR.PAZ.SAN.TİC.LTD.ŞTİ
CEYHAN YOLU 15.KM. ADANA/TURKEY

GENEL BİLGİLER / GENERAL INFORMATION

Üretici Adı manufacturer name	RMA YATIRIM MAK.İNŞ.SAN.VE TİC.LTD .ŞTİ		
Ürün Adı Product Series	POLİETİLEN WATER TANKS		
Üretim Tarihi Production Date	30.12.2015	Test /rapor no Test raport no	30122015-1
Markalama Branding	RMA		
Ülke Country of origin	TÜRKİY	Net kapasite Net capacity in liters	500 lt

ÖLÇÜMLER / MEASUREMENTS

Boyut Kontrolü Size control 2295 IQS TYP 1 TABLO 1	Genişlik Width	Et Kalınlığı Wall thickness	Uzunluk Length	Ağırlık Weight (kg)	Test sonucu/ Test Result
500 LT X 6,0 mm	29	7,1	80	21	Olumlu

TEST VERİLERİ / TEST DATA

Boyut Kontrolü Size control 2295 IQS TYP 1 TABLO 1	Genişlik Width	Uzunluk Length	
500 LT X 6,0 mm	29	80	
Uzama Direnç Resistance to Elongation	12N/mm ²	12,02 N/mm ²	Olumlu
Deformasyon Etkisi Resistance to Deformation D_L = deformation of the longer side, D_W = deformation of the shorter side, 2295 IQS 7.2 12701; ANNEX B (Clauses 7.1.1 and 7.1.2) 500LT POLİETİLEN WATER TANKS	The difference of circumference shall not exceed 2 % of the original circumference of closed top vertical cylindrical tanks, and for open top vertical cylindrical tanks. Difference of length and width shall not exceed 3 % for parallelepiped tanks. Difference in length and circumference shall not exceed 3 % of the original length and circumference for horizontal cylindrical tanks when tested according to the specific standard.		Olumlu
Dirence karşı Eğilme Resistance to bending 2295 IQS 4.13 **7.2 500 LT POLİETİLEN WATER TANKS	Resistance to bending of tank walls shall not be less than 400 N / mm ² when tested according to the specific standard		Olumlu
Bağlantılar Connections	Manşon's		

PLASTSU
PLASTİK
LABORATUVAR
KONTROL EDİLMİŞTİR

Rogar Kapağı The manhole cover	The manhole cover shall be of polyethylene according		Olumlu
Bitirme Finishing	The internal and external surfaces of the tank shall be smooth ,clean ,and free of internal defects such as air bubbles,holes and other foreign matter		Olumlu
Direnç Üsten Yükleme resistance to load from the top **7.2 IQS 2295 500 LT POLİETİLEN WATER TANKS	The tank shall be examined for signs of deformation or cracking. The surface shall return to its normal position after 4 hours from the lifting of the load when tested according to the specific standard	HASAR OLUŞMADI	Olumlu
Darbe Dayanımı Resistance to Impact	There wasn't any damage		Olumlu
Test Yapan Test Done By	Hacer Mumcuoglu	Onaylayan Approved By	
İmza Signature		İmza Signature	



PLASTSU®
PLASTİK

İMALAT İHR. PAZ. SAN. TİC. LTD. ŞTİ.
Ceylan Yolu Üzeri 15. Km. 01310 ADANA / TÜRKİYE
T. 0322 325 25 00 F. 0322 325 25 12
GİRİŞ VERGİ Dairesi V.N. : 730 013 7416
plastsu.com.tr www.plastsu.com.tr